Research Article Nanotechnology



#### **International Journal of Pharma and Bio Sciences**

ISSN 0975-6299

# BIOMIMETIC SYNTHESIS OF SILVER NANOPARTICLES USING AQUEOUS EXTRACT OF AMARANTHUS POLYGONOIDES

#### M. JANNATHUL FIRDHOUSE\*1 AND P. LALITHA2

<sup>1</sup> PhD Scholar, Department of Chemistry, Avinashilingam Institute for Home Science and Higher Education for Women University, Coimbatore – 641043, Tamil Nadu, India.

<sup>2</sup> Assistant Professor (Senior Scale), Department of Chemistry, Avinashilingam Institute for Home Science and Higher Education for Women University, Coimbatore – 641043, Tamil Nadu, India.

#### **ABSTRACT**

Green nanotechnology involves the application of green chemistry principles to design nanoscale particles, developing facile method of synthesis and its application. This approach aims to synthesize silver nanoparticles using the aqueous extract of *Amaranthus polygonoides*. The formation of silver nanoparticles was confirmed by UV Visible spectroscopy, X-ray diffraction, use of Scherrer's equation Scanning Electron Microscopy and Fourier transform infrared spectroscopy. The size of synthesized silver nanoparticle was found to be less than 50nm.

KEY WORDS: Amaranthus polygonoides, Nanoparticles, SEM, FTIR, XRD



#### M. JANNATHUL FIRDHOUSE

PhD Scholar, Department of Chemistry, Avinashilingam Institute for Home Science and Higher Education for Women University, Coimbatore – 641043, Tamil Nadu, India.

#### INTRODUCTION

Nanotechnology deals with the development of experimental processes for the synthesis of nanoparticles of different sizes, shape and controlled dispersity. Nanoscale materials and structures are usually ranging from 1-100 nm and is an emerging area of nanoscience and nanotechnology. **Synthesis** of nanoparticles for the applications such as catalysis, electronics. environmental biotechnology is an area of constant interest<sup>1</sup>. Recently, green nanoparticle synthesis has become an important branch of nanotechnology owing to its potential application in biomedical, magnetics, energy science and aerospace industries. Large amounts of nanoparticles can be easily synthesized from plants and the majority of these are nontoxic<sup>2</sup>. The biosynthesis of silver nanoparticles has been reported using bacteria <sup>3</sup>, fungi <sup>4</sup>, plants, and plant extract 5-8. For several years, scientists have constantly explored different synthetic methods to synthesize nanoparticles. Chemical synthesis involves toxic solvents, high pressure, energy and high temperature conversion. Also microbe involved synthesis is not feasible due to its lab maintenance . Green methods of synthesis of nanoparticles are easy, efficient, and eco-friendly in comparison to chemical-mediated or microbe-mediated synthesis. An eco-biological approach to the synthesis of silver nanoparticles is an eco-friendly and costeffective method as compared to the other physical methods. Several chemical and antibiotics use silver compounds such as metallic silver, silver nitrate, silver sulfadizine for treatment of burns, wounds and several bacterial infections  $^{10}$ . The silver nanoparticles and Ag+ carriers can be beneficial in delayed diabetic wound healing as diabetic wounds are affected by many secondary infections. These nanoparticles can help the diabetic patients in early wound healing with minimal scars. Silver nitrate is still a common antimicrobial used in the treatment of chronic wounds 11. This has promoted research in the well known activity of silver ions and silver-based compounds. including silver nanoparticles. Amaranth "the crop of the future", has been proposed as an inexpensive native crop that could be cultivated

by indigenous people in rural areas for several reasons. It is easily harvested, highly tolerant of arid environments, which are typical of most subtropical and tropical regions and seeds are a good source of protein, rich in essential amino acids. Amaranthus polygonoides is a species of flowering plant. It goes by the common name of Tropical Amaranth. In the synthesis nanoparticles chemical methods of synthesis are more common. This may not be economical and eco-friendly. Use of Amaranth makes the process highly economical. In the present work, we report a low cost, non- toxic and easy synthesis of silver nanoparticles by the reduction of silver ions using the aqueous extract of Amaranthus polygonoides under various experimental conditions.

#### MATERIALS AND METHODS

#### (i) Preparation of the extract

The fresh leaves of *Amaranthus polygonoides* (20g) were washed thrice thoroughly with double distilled water. Leaves were finely cut and boiled for 5mins with 100 ml of distilled water in a 500 ml Erlenmeyer flask. The prepared extract was filtered through Whatman filter paper and stored at -4° C for further experiments.

### (ii) Synthesis of silver nanoparticles

The aqueous extract of *Amaranthus* polygonoides was treated with aqueous solution of 3mM silver nitrate under various experimental conditions.

#### a) Conventional method

The plant extract (1ml) was mixed with different concentrations (6ml, 7ml, 8ml, 9ml and 10ml) of silver nitrate solutions and kept at room temperature.

## b) Higher temperature method

Different concentrations (6ml, 7ml, 8ml, 9ml and 10ml) of silver nitrate solutions and aqueous

extract (1ml) were maintained at a temperature (75°C) using steam bath, till the formation of silver nanoparticles.

#### c) Sonication method

Different concentrations (6ml, 7ml, 8ml, 9ml and 10ml) of aqueous silver nitrate and plant extract were sonicated using ultrasonic bath (PCI Ultrasonics 1.5 L (H) till the formation of silver nanoparticles.

#### (iii) Separation of silver nanoparticles

The reddish brown silver solution was centrifuged (Spectrofuge 7M) at 13000 rpm for 15 minutes and again redispersed the particles and centrifugation. The supernatant solutions were analyzed for further experiments.

# (iv) Characterization of silver nanoparticles

### a. UV-visible spectra analysis

The bioreduction of silver ions in aqueous solution was monitored by UV-visible spectra of the supernatant solution as a function of time at room temperature using Double beam spectrophotometer 2202 (Systronics).

#### b. XRD analysis

X-ray diffraction (XRD) analysis of drop-coated films of silver nanoparticles in a glass substrate was prepared for the determination of the formation of Ag nanoparticle by an Lab X XRD-6000 (Shimadzu) operated at a voltage of 40 kV and a current of 30 mA with Cu K $\alpha$  radiation.

# c. Determination of crystalline size of AqNPs

XRD patterns were analyzed to determine peak intensity, position and width. Fullwidth at half maximum (FWHM) data, was used with the Scherrer's formula to determine mean particle size. The Scherrer's equation is given by D=  $0.94\lambda/\beta\cos\theta$  where d is the mean diameter of the nanoparticles,  $\lambda$  is wavelength of X-ray radiation source,  $\beta$  is the angular FWHM of the XRD peak at the diffraction angle  $\theta$  in radians <sup>12-</sup>

### d. SEM observation of silver nanoparticles

SEM samples of the aqueous suspension of silver nanoparticles were fabricated by dropping the suspension onto glass substrate and allowing water to completely evaporate. SEM observations were carried out on a TESCAN Electron microscope (Vega TC software).

#### e. FTIR analysis of silver nanoparticles

The aqueous solution of synthesized silver nanoparticles after centrifugation was analyzed by FTIR spectrum (Bruker FTIR Tensor-27).

Green synthesis of silver nanoparticles using

#### RESULTS AND DISCUSSIONS

3mM AqNO<sub>3</sub> and different volume fractions of aqueous extract of Amaranthus polygonoides are shown in (Fig 1). (Fig 2) shows the characteristic surface plasmon resonance (SPR) absorption band at 425nm for reddish brown silver nanoparticles as 1ml of plant extract solution is used. Silver NPs have unique optical properties because they support surface plasmons. At specific wavelengths of light the surface plasmons are driven into resonance and the AgNPs have a distinct color that is a function of their size, shape and environment 14-<sup>15</sup> A concentration variation study of AgNO<sub>3</sub> using aqueous extract was carried out under various conditions. (Fig 2) shows that increasing intensity of 425nm SPR band with increasing concentration of AgNO<sub>3</sub>, another band at 465nm is appeared. Increasing intensity of the SPR 425nm band indicates increasing concentration of particle. It is observed that the surface plasmon resonance band occurs at 425 nm and steadily increases in intensity as a function of concentration. To optimize the reaction time, a time variation study was carried out using the optimized concentration of aqueous extract (1ml) and silver nitrate shown in (fig 3). From this figure, it is guite evident that the rapid biosynthesis of silver nanoparticles can be achieved at higher temperatures compared to conventional and sonication methods.




Figure 1

Amaranthus polygonoides- Colour change of extract containing Ag before (a)

and after synthesis of Ag nanoparticles (b)




Figure 2
UV-Visible spectra absorption spectra of silver nanoparticles from extract of Amaranthus polygonoides and silver nitrate solution at different concentrations




Figure 3
Comparative studies of different methods as a function of time

(Fig 4) shows that the XRD patterns of drop coated silver nanoparticles synthesized using aqueous extract of *Amaranthus polygonoides*. The XRD pattern showed three intense peaks of Bragg reflections with  $2\theta$  values of  $27.38^{\circ}$ ,  $31.95^{\circ}$  and  $38.40^{\circ}$  set of lattice planes are observed which may be indexed to the (220), (101) and (111) based on face centered cubic

structure of silver respectively (JCPDS no. 04-0783) <sup>16-17</sup>. XRD pattern thus clearly illustrates that the silver nanoparticles formed in this present synthesis are crystalline in nature. The average size of the silver nanoparticles was estimated from the FWHM of the (111) peak using the Scherrer's formula is 16.03nm is given in table.1.




Figure 4

XRD pattern of drop coated silver nanoparticles synthesized using aqueous extract of Amaranthus polygonoides.

Table 1
Determination of crystalline size of AgNP's by using Debye-Scherrer's equation

S.No	2θ	FWHM	$\beta = \pi^* FWHM/180$	D = $k \lambda / \beta$ . Cosθ
1.	31.9594	0.6188	0.01079	13.37
2.	27.3500	1.2250	0.02136	6.68
3.	38.4000	0.3000	0.00523	28.05

Average size of the nanoparticle = 13.37 + 6.68 + 28.05 / 3 = 16.03nm

SEM micrograph recorded from a drop coated films of silver nanoparticles synthesized using aqueous extract of *Amaranthus polygonoides* after reaction with silver nitrate solution shows

that the sample composed of large number of silver nanoparticles (fig 5). The diameter of the silver nanoparticles was in the range from 40-50 nm, possessing spherical shape.




Figure 5
SEM micrograph of drop coated silver nanoparticles synthesized using Aqueous extract of Amaranthus polygonoides.

The FTIR spectra of the synthesized silver nanoparticles from aqueous extract of *A. polygonoides* in (fig 6) shows the presence of various functional groups. The peaks located at 1595 and 1484 cm<sup>-1</sup> are associated with the stretching vibrations of –C–C– in aromatic ring. The vibration frequencies at 1667 cm<sup>-1</sup>, 2422

cm<sup>-1</sup> and 2507 cm<sup>-1</sup> are assigned as absorption peaks of CN double and triple bonds respectively. Thus the presence of above functional groups revealed that the amide groups in protein linkage of the extract may be responsible for the reduction of silver ions.




Figure 6

FTIR spectra of the synthesized silver nanoparticles from aqueous extract of A. polygonoides

#### CONCLUSION

A facile method of synthesizing silver nanoparticles from the aqueous extract of *A. polygonoides* under various experimental conditions is reported. The concentration of silver nitrate and the aqueous extract of *A. polygonoides* play an important role in size and shape of the synthesized silver nanoparticles.

Comparative study of various methods revealed that high temperature method results in rapid synthesis of silver nanoparticles. The size of the nanoparticle was found to be less than 50 nm possessing spherical shape which was confirmed by XRD and SEM analysis.

#### **ACKNOWLEDGEMENT**

The authors sincerely thank the Avinashilingam Institute for Home Science and Higher Education for Women University, Coimbatore, Tamilnadu, for providing research facilities, Karunya University for recording XRD and Periyar Maniammai University for recording SEM.

#### REFERENCES

- 1. Masurkar SA, Chaudhari PR, Shidore VB, and Kamble SP, Rapid Biosynthesis of Silver Nanoparticles using *Cymbopogan Citratus* (Lemongrass) and its antimicrobial activity. Nano-Microletters, 3(3): 189-194, (2011).
- Elavazhagan T and Arunachalam KD, Memecylon edule leaf extract mediated
- green synthesis of silver and gold nanoparticles. International Journal of Nanomedicine, 6: 1265-1278, (2011).
- 3. Lengke MF, Fleet ME and Southam G, Biosynthesis of Silver Nanoparticles by Filamentous Cyanobacteria from a silver (I) nitrate Complex. Langmuir, 4(3): 537-543, (2007).

- Mukherjee P, Ahamad A, Mandal D, Senapati S, Sainkar SR, Khan MI, Praishcha R, Ajaykumar PV, Alam M, Kumar R and Sastry R, Fungus-Mediated Synthesis of Silver Nanoparticles and their immobilization in the Mycelial Matrix: A Novel Biological Approach to Nanoparticle Synthesis. Nanoletters, 1(10): 515-519, (2001).
- 5. Sarkar R, Kumbhakar P and Mitra AK, Green Synthesis of Silver Nanoparticles and its Optical properties. Digest Journal of Nanomaterials and Biostructures, 5(2): 491 496, (2010).
- 6. Singh A, Jain D, Upadhyay MK, Khandelwal N and Verma HN, Green synthesis of silver nanoparticles using *Argemone Mexicana* leaf extract and evaluation of their antimicrobial activities. Digest Journal of Nanomaterials and Biostructures. 5(2): 483-489, (2010).
- 7. Prabhu N, Divya TR, Yamuna Gowri K, Ayisha Siddiqua S and Joseph Puspha Innocent S, Synthesis of silver phyto nanoparticles and their antibacterial efficacy. Digest Journal of Nanomaterials and Biostructures. 5(1): 185 189, (2010).
- 8. Parashar UK, Saxena PS and Srivastava A, Bioinspired synthesis of silver nanoparticles. Digest Journal of Nanomaterials and Biostructures, 4 (1): 159-166, (2009).
- 9. Mubayi A, Chatterji S, Rai PK, and Watal G, Evidence based green synthesis of

- nanoparticles. Advanced Materials Letters, doi: 10.5185/amlett.2012.icnano.353.
- 10. Arya V, Komal R, Kaur M and Goyal A, Silver nanoparticles as a potent antimicrobial agent: A Review. Pharmacologyonline. 3: 118-124, (2011).
- 11. Gupta A and Silver S, Silver as a biocide: will resistance become a problem? Nat. Biotechnol., 16: 888, (1988).
- 12. Cullity BD, Elements of X-ray Diffraction, (2nd edn), Edison-Wesley Publishing Company
- 13. Inc, USA, (1978).
- 14. Jeffrey JW, Methods in crystallography, Academic press, New York (1971).
- 15. Noguez C, Surface plasmons on metal nanoparticles: The influence of shape and physical environment. J Phys Chem C., 111: 3806–3819, (2007).
- Rosarin FS and Mirunalini S, Nobel Metallic Nanoparticles with Novel Bio-medical Properties. J Bioanal Biomed., 3: 85-91, (2011).
- 17. Varshney R, Mishra AN, Bhadauria S, and Gaur MS, A novel microbial route to synthesize silver nanoparticles using Fungus *Hormoconis Resinae*. Digest Journal of Nanomaterials and Biostructures, 4 (2): 349-355, (2009).
- 18. Vivek M, Senthilkumar P, Staffi S and Sudha S, Biogenic Silver Nanoparticles by *Gelidiella acerosa* extract and their Antifungal effects. Avicenna Journal of Medical Biotechnology, 3(3): 143-148, (2011).